

## AÇOS LIGADOS

AISI/SAE	C	Mn	Ni	Cr	Mo	Outros elementos
1330	.28 / .33	1.60 / 1.90	-	-	-	-
1335	.33 / .38	1.60 / 1.90	-	-	-	-
1340	.38 / .43	1.60 / 1.90	-	-	-	-
1345	.43 / .48	1.60 / 1.90	-	-	-	-
4130	.28 / .33	.40 / .60	-	.80 / 1.10	.15 / .25	-
4135	.33 / .38	.70 / .90	-	.80 / 1.10	.15 / .25	-
4140	.38 / .43	.75 / 1.00	-	.80 / 1.10	.15 / .25	-
4150	.48 / .53	.75 / 1.00	-	.80 / 1.10	.15 / .25	-
4320	.17 / .22	.45 / .65	1.65 / 2.00	.40 / .60	.20 / .30	-
4340	.38 / .43	.60 / .80	1.65 / 2.00	.70 / .90	.20 / .30	-
5120	.17 / .22	.70 / .90	-	.70 / .90	-	-
5130	.28 / .33	.70 / .90	-	.80 / 1.10	-	-
5135	.33 / .38	.60 / .80	-	.80 / 1.05	-	-
5140	.38 / .43	.70 / .90	-	.70 / .90	-	-
5147	.46 / .51	.70 / .95	-	.85 / 1.15	-	-
5150	.48 / .53	.70 / .90	-	.70 / .90	-	-
5155	.51 / .59	.70 / .90	-	.70 / .90	-	-
5160	.56 / .64	.75 / 1.00	-	.70 / .90	-	-
E 52100	.98 / 1.10	.25 / .45	-	1.30 / 1.60	-	-
						<b>V</b>
6118	.16 / .21	.50 / .70	-	.50 / .70	-	.10 / .15
6150	.48 / .53	.70 / .90	-	.80 / 1.10	-	.15 mín.
8615	.13 / .18	.70 / .90	.40 / .70	.40 / .70	.15 / .25	-
8617	.15 / .20	.70 / .90	.40 / .70	.40 / .60	.15 / .25	-
8620	.18 / .23	.70 / .90	.40 / .70	.40 / .60	.15 / .25	-
8622	.20 / .25	.70 / .90	.40 / .90	.40 / .60	.15 / .25	-
8625	.23 / .28	.70 / .90	.40 / .70	.40 / .60	.15 / .25	-
8627	.25 / .30	.70 / .90	.40 / .70	.40 / .60	.15 / .25	-
8630	.28 / .33	.70 / .90	.40 / .70	.40 / .60	.15 / .25	-
8637	.35 / .40	.75 / 1.00	.40 / .70	.40 / .60	.15 / .25	-
8640	.38 / .43	.75 / 1.00	.40 / .70	.40 / .60	.15 / .25	-
8642	.40 / .45	.75 / 1.00	.40 / .70	.40 / .60	.15 / .25	-
8645	.43 / .48	.75 / 1.00	.40 / .70	.40 / .60	.15 / .25	-
8650	.48 / .53	.75 / 1.00	.40 / .70	.40 / .60	.15 / .25	-
8655	.51 / .59	.75 / 1.00	.40 / .70	.40 / .60	.15 / .25	-
8660	.56 / .64	.75 / 1.00	.40 / .70	.40 / .60	.15 / .25	-
						<b>Si</b>
9254	.51 / .59	.60 / .80	-	.60 / .80	-	1.20 / 1.60
9260	.56 / .64	.75 / 1.00	-	-	-	1.80 / 2.20
9310	.08 / .13	.45 / .65	3.00 / 3.50	1.00 / 1.40	.08 / .15	-

