

AÇOS CARBONO

AISI/SAE	C	Mn	P Máx.	S Máx.
1005	.06 máx.	.35 máx.	.040	.050
1006	.08 máx.	.25 / .40	.040	.050
1008	.10 máx.	.30 / .50	.040	.050
1010	.08 / .13	.30 / .60	.040	.050
1012	.10 / .15	.30 / .60	.040	.050
1020	.18 / .23	.30 / .60	.040	.050
1022	.18 / .23	.70 / 1.00	0.40	.050
1025	.22 / .28	.30 / .60	.040	.050
1030	.28 / .34	.60 / .90	.040	.050
1035	.32 / .38	.60 / .90	.040	.050
1040	.37 / .44	.60 / .90	.040	.050
1045	.43 / .50	.60 / .90	.040	.050
1050	.48 / .55	.60 / .90	.040	.050
1055	.50 / .60	.60 / .90	.040	.050
1060	.55 / .65	.60 / .90	.040	.050
1065	.60 / .70	.60 / .90	.040	.050
1070	.65 / .75	.60 / .90	.040	.050
1075	.70 / .80	.40 / .70	0.40	.050
1080	.75 / .88	.60 / .90	.040	.050
1085	.80 / .93	.70 / 1.00	.040	.050
1090	.85 / .98	.60 / .90	.040	.050
1095	.90 / 1.03	.30 / .50	.040	.050

